

## Moplen HP520M

Polypropylene Homopolymer Resin for core layer of Co-extrusion

### Features

- Good optical properties
- Good film stiffness
- Low gels
- Excellent compatibility with multi-layer film constructions

### Typical applications

- As core layer for co-extrusion cast films
- Ribbon Tape

Resin properties (a)	Moplen HP520M	ASTM METHOD(b)
Melt flow rate (230 °C / 2.16 kg), dg/min	8	D1238
Density, g/cm <sup>3</sup>	0.90	D792B
Tensile strength at yield, MPa	35	D638
Elongation at yield, %	10	D638
Flexural modulus, MPa	1550	D790A
Notched izod impact strength at 23 °C, J/m	28	D256A
Deflection temperature, at 455 kPa, °C	105	D648

(a) Values shown are averages and are not to be considered as specifications.

(b) ASTM test methods are the latest under Society's current procedures. All molded specimens are prepared by injection

### Chemical Registration / Inventory Status

All ingredients in *Moplen* HP520M meet the chemical registration requirements of TSCA (U.S.) and DSL (Canada).

Note: Due to the fact that different regulations in each country set different details of compliance, users of *Moplen* HP520M are recommended to undertake their own investigation of the requirements and comply with each regulation set forth, for instance, in applicable local F&DA requirements. Ultimately the users must make their own determination that their use of *Moplen* HP520M is safe, lawful and technically suitable in their intended applications.

*Moplen* is a trademark of LyondellBasell Industries

HMC Polymers is certified according to ISO 9001 and 14001

Issued 1-Aug-08

**The purpose of this document is only for technical support of the use of the product.**

Before using a HMC Polymers product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the HMC Polymers product safely and legally. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under HMC Polymers', LyondellBasell's or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of HMC Polymers except in a writing signed by an authorized HMC Polymers employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at HMC Polymers' option, and in no event shall HMC Polymers be liable for special, consequential, incidental, punitive or exemplary damages.

### HMC Polymers Co., Ltd

20/F, Sathorn City Tower, 175 South Sathorn Road, Thungmahamek, Sathorn, Bangkok 10120, Thailand

Tel +66 2679 6388-89, 2614 3700 Fax +66 2679 6380

[www.hmcpolymers.com](http://www.hmcpolymers.com)

